

Induprint SE 908

Provisional Data Sheet

- ◆ Emulsion polymer based on styrene and acrylates

Fields of Application: Printing Inks, Overprint Varnishes and Coatings

- ◆ Let-down vehicle for water-based flexographic and gravure-printing inks
- ◆ Binder for water-based overprint varnishes

Characteristics:

- ◆ high gloss
- ◆ good heat resistance
- ◆ fast drying
- ◆ free of glycols and glycol ethers

Appearance	:	whitish emulsion	
Solid Contents * (DIN EN ISO 3251)	:	47 – 49 %	
Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=28.9 s ⁻¹)	:	450 – 900 mPa·s	I
pH Value * (DIN ISO 976)	:	8.0 – 8.6	
Glass Temperature (DSC) (DIN 51007)+	:	appr. + 100°C	
Acid Value	:	appr. 65 mg KOH/g solid	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	stable	
			2017-05-04
* Specification values listed in our certificate of analysis			

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.