

# Indunal ECR 774 L

- ◆ Aqueous solution of polysodium styrene sulfonate

**Fields of Application:**     **Architectural Coatings, Printing Inks, Wood Finishing, Personal Care, Paper Finishing, Pigment Concentrates**

- ◆ Electroconductive resin for dielectric papers and films
- ◆ Anionic antistatic agent
- ◆ Flow agent for paints and lacquers
- ◆ Polymeric surfactant for cosmetic products
- ◆ Dispersing agent for inorganic and organic pigments

**Performance:**

- ◆ excellent antistatic effect
- ◆ very good substrate and pigment wetting

<b>Appearance</b>	:	transparent yellowish solution
<b>Solid Contents</b> * (DIN EN ISO 3251)	:	29 – 31 %
<b>Viscosity</b> * at 20°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=28.9 s <sup>-1</sup> )	:	120 - 440 mPa·s
<b>pH Value</b> * (DIN ISO 976)	:	6.0 – 10.0
<b>Ionicity</b>	:	anionic
<b>Freeze/Thaw Stability</b>	:	stable
2024-03-21		
* Specification values listed in our certificate of analysis		

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.