

Induprint PAC 4212 H

- ◆ Aqueous solution polymer based on methacrylates, carboxylated

Fields of Application: **Printing Inks**

- ◆ Let-down vehicle for water-based flexographic and gravure-printing inks (for gift wrapping, tissue, wallpaper)

Characteristics:

- ◆ excellent resolubility
- ◆ high alkali resistance
- ◆ low odour, free of amines
- ◆ very good transfer

Appearance	:	cloudy, pale yellowish solution	I
Solid Contents * (DIN EN ISO 3251)	:	32 - 34 %	
Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=9.24 s ⁻¹) decrease of viscosity during storage time	:	700 - 1500 mPa·s 24 h after the production	I
pH Value * (DIN ISO 976)	:	8.8 – 9.5	
Glass Temperature (DSC) (DIN 51007)	:	appr. + 110°C	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	stable	
			2020-07-29
* Specification values listed in our certificate of analysis			

please turn

Induprint PAC 4212 H

Remarks:

Induprint PAC 4212 H is free of solvents and coalescing agents.

Induprint PAC 4212 H provides better resolubility and faster drying than Induprint PAC 4205 HHV and Induprint PAC 4206 H. Induprint PAC 4212 H exhibits faster drying than Induprint PAC 4211 H.

Alkali resistance of the printing inks may be improved by blending Induprint PAC 4212 H with alkali resistant low MFFT polymers.

Starting Formulations:

No. 138 Printing Ink for tissue application
No. 151 Printing Ink for tissue application

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.