

Induprint PAC 6651

- ◆ Emulsion polymer based on methacrylates

Fields of Application: **Printing Inks**

- ◆ Let-down vehicle for alkali-resistant water-based flexographic and gravure-printing inks (i.e. for tissue) in combination with hydrosols of **Induprint PAC 4201 S**

Characteristics:

- ◆ excellent alkali resistance
- ◆ low odour
- ◆ high viscosity

Appearance	:	white emulsion	
Solid contents* (DIN EN ISO 3251)	:	48 – 50 %	
Viscosity* at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=9.24 s ⁻¹)	:	1000 - 2300 mPa·s	I
pH Value * (DIN ISO 976)	:	8.0 - 9.0	
MFFT (DIN ISO 2115)	:	appr. 0°C	
Glass Temperature (DSC) (DIN 51007)	:	appr. + 3°C	
Acid Value	:	appr. 15 mg KOH/g solid	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	unstable	
			2020-07-22
* Specification values listed in our certificate of analysis			

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.