

Induprint SE 90

- ◆ Emulsion polymer based on styrene and acrylates

Fields of Application: **Printing Inks, Overprint Varnishes and Coatings**

- ◆ Binder for water-based overprint varnishes
- ◆ Let-down vehicle for water-based flexographic and gravure-printing inks

Characteristics:

- ◆ high heat resistance
- ◆ excellent gloss
- ◆ free of glycols or glycol ethers
- ◆ VOC < 0.05%

Appearance	:	white emulsion	
Solid Contents * (DIN EN ISO 3251)	:	44 - 46 %	
Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D= 38.7 s ⁻¹)	:	100 - 250 mPa·s	I
Viscosity DIN 4 cup at 20°C	:	40 – 70 sec	
pH Value * (DIN ISO 976)	:	7.8 – 8.8	
Glass Temperature (DSC) (DIN 51007)	:	appr. + 99°C	
Acid Value	:	appr. 74 mg KOH/g solid	I
MFFT (DIN ISO 2115)	:	appr. + 86°C	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	stable	
			2003-01-27 / Version 08
* Specification values listed in our certificate of analysis			

please turn

Induprint SE 90

Remarks:

Apart from the mentioned properties Induprint SE 90 provides an excellent transfer, very good hold-out, fast drying and low foaming properties. The product is free of solvents and coalescing agents.

Induprint SE 90 is a very hard polymer. It is therefore necessary to modify the polymer by addition of coalescing agents (i.e. Dowanol DPM) or softer polymers to enable film formation and gloss improvement at normal operating temperatures.

Gloss improvement or a softer varnish may be obtained by the combination of Induprint SE 90 with Induprint SE 245 or Induprint SE 1985.

Further improvement of the heat-seal resistance is possible by adding Indunal Z 15 (ZnO solution).

Starting Formulations:

No. 258 low solid matt opv
No. 259 low solid glossy opv
No. 260 High gloss opv

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.