

# Makrovil D 3630

- ◆ Emulsion polymer based on styrene and acrylates

## Fields of Application:    **Architectural Coatings**

- ◆ binder for sealants
- ◆ binder for plasticizing of mortars and plasters
- ◆ binder for fillers

## Characteristics:

- ◆ excellent flexibility
- ◆ very good alkali resistance

<b>Appearance</b>	:	white emulsion	
<b>Solid contents*</b> (DIN EN ISO 3251)	:	56 – 58 %	
<b>Viscosity *</b> at 25°C (DIN 53019-1) (Anton Paar Rheolab QC; MS: CC 27; D = 180 s <sup>-1</sup> )	:	30 - 200 mPa·s	I
<b>pH Value *</b> (DIN ISO 976)	:	7.5 - 9.0	
<b>MFFT</b> (DIN ISO 2115)	:	< 0°C	
<b>Glass transition temperature</b>	:	appr. – 9°C	
<b>Protective Colloid</b>	:	surfactants	
<b>Ionicity</b>	:	anionic	
<b>Freeze/Thaw Stability</b>	:	unstable	
			2020-07-22
* Specification values listed in our certificate of analysis			

**please turn**

# Makrovil D 3630

## Starting formulation:

No. 66	Kitt
No. 241	folding adhesives
No. 256	matt high COF opv
No. 257	glossy high COF opv

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.