

Makrovił PAC 114

- ◆ Styrene-acrylic copolymer emulsion

Fields of Application: **Architectural Coatings**

- ◆ Binder for emulsion paints and plasters
- ◆ Binder for concrete coatings
- ◆ Binder for lutes and filling compounds

Characteristics:

- ◆ excellent flexibility
- ◆ very good pigment wetting power

Appearance	:	white emulsion	
Solid Contents * (DIN EN ISO 3251)	:	47 - 49 %	
Viscosity * at 25°C (DIN 53019-1) (Anton Paar Rheolab QC; MS: CC27; D= 28.9 s ⁻¹)	:	350 - 1000 mPa·s	I
pH Value * (DIN ISO 976)	:	7.8 – 8.8	
MFFT (DIN ISO 2115)	:	appr. + 8°C	
Protective Colloid	:	surfactants	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	unstable	
			2020-07-21
* Specification values listed in our certificate of analysis			

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.