

Makrovil PAC 6178

- ◆ Emulsion polymer based on acrylates and methacrylates

Fields of Application: **Architectural Coatings**

- ◆ Binder for water-based gravure and blocking primers
- ◆ on mineral surfaces

Characteristics:

- ◆ excellent Penetration
- ◆ very good strengthening of substrate
- ◆ finely dispersed

Appearance	:	semi-transparent emulsion
Solid Contents * (DIN EN ISO 3251)	:	32.0 – 34.0 % I
Viscosity * at 20°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=121 s ⁻¹)	:	< 200
pH Value * (DIN ISO 976)	:	8.2 – 8.7
MFFT (DIN ISO 2115)	:	appr. 0°C
Glass Temperature (DSC) (DIN 51007)	:	appr. + 7°C
Protective Colloid	:	active surfactants
Ionicity	:	anionic
Freeze/Thaw Stability	:	stable
2018-03-15		
* Specification values listed in our certificate of analysis		

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.

Makrovil PAC 6178

Starting formulation:

No. 51 water based sealing primer