

Makrovil V 344

Homopolymeric emulsion based on vinyl acetate

Fields of Application: **Textile Finishing, Adhesives**

- Binder for textile stiffeners and laundry starches
- Raw material for wood and paper adhesives

Characteristics:

very high solubility in water

Appearance white emulsion

Solid Contents * (DIN EN ISO 3251) 53 - 55 %

Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=9.24 s $^{-1}$) 1000 - 2000 mPa·s

pH Value * (DIN ISO 976) 4.5 - 5.5

MFTT (DIN ISO 2115) appr. + 16°C

Glass Temperature (DSC) appr. + 41°C

(DIN 51007)

Protective Colloid Polymers

Ionicity nonionic

Freeze/Thaw Stability unstable

2020-07-21

please turn

^{*} Specification values listed in our certificate of analysis



Makrovil V 344

Starting formulation:

No. 85 laundry starch

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.