Induprint SE 2954

- Soft emulsion polymer based on styrene and acrylates

Fields of Application: **Printing Inks and Overprint Varnishes**

- Binder for glossy water-based overprint varnishes
- Let-down vehicle for water-based flexographic and gravure-printing inks (i.e. used on films)

Characteristics:

- excellent gloss
- very high flexibility
- very good adhesion on films

Appearance	:	white to pale brownish emulsion
Solid Contents* (DIN EN ISO 3251)	:	39 – 41 %
Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D=28.9s^{-1})	:	650 - 1700 mPa·s
pH Value * (DIN ISO 976)	:	8.0 – 8.6
Glass Temperature (DSC) (DIN 51007)	:	< - 40°C
Acid Value	:	appr. 76 mg KOH/g solid
MFFT (DIN ISO 2115)	:	< 0°C
Ionicity	:	anionic
Freeze/Thaw Stability	:	stable

2026-09-30

* Specification values listed in our certificate of analysis

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.

Indulor Chemie GmbH . Schulstraße 3 . 49577 Ankum . Germany . Fon +49 5462 7412-0 . Fax +49 5462 7412-74 . E-Mail: info@indulor.de
Indulor AG . Industriestraße 49 . 6300 Zug . Switzerland . Fon +41 41 76899-88 . Fax +41 41 76899-89 . E-Mail: info@indulor.de