

Induprint S 1033

- ◆ Ammonia-solubilised resin solution

Fields of Application: Printing Inks and Overprint Varnishes

- ◆ Vehicle for water-based overprint varnishes and flexographic and gravure-printing inks

Performance and Characteristics:

- ◆ Gloss improvement
- ◆ Increase of transfer and resolubility
- ◆ Improvement of the block resistance
- ◆ free of glycols and glycol ethers

Appearance	:	transparent, nearly colourless solution	
Solid Contents * (oven, 1h, 130°C)	:	32 - 33 %	
Viscosity * at 25°C (DIN 53019-1) (Anton Paar RheolabQC; MS: CC27; D= 28.9 s ⁻¹)	:	1000 - 1800 mPa·s	I
pH Value * (DIN ISO 976)	:	7.9 – 8.3	
Glass Temperature (DSC) (DIN 51007)	:	appr. + 105°C	
Acid Value calculated on solids	:	appr. 222 mg KOH/g	
Ionicity	:	anionic	
Freeze/Thaw Stability	:	stable	
			2024-03-06
* Specification values listed in our certificate of analysis			

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.