

## **Makrovil PAC 80**

Provisional Data Sheet

♦ Pure-acrylic copolymer emulsion

## Fields of Application: **Architectural Coatings**

- Binder for emulsion paints and plasters
- Binder for concrete coatings

## **Characteristics:**

- very good water and alkali resistance
- excellent flexibility
- good pigment wetting power

white emulsion **Appearance** 

Solid Contents \* (DIN EN ISO 3251) 47 - 49 %

**Viscosity** \* at  $25^{\circ}$ C (DIN 53019-1) (Anton Paar Rheolab QC; MS: CC27; D=  $28.9 \text{ s}^{-1}$ ) 100 - 500 mPa·s

pH Value \* (DIN ISO 976) 8.0 - 9.0

MFFT (DIN ISO 2115) appr. + 5°C

**Protective Colloid** surfactants

Ionicity anionic

Freeze/Thaw Stability unstable

2024-03-18

This data sheet is for your advice and information. Indulor disclaims any liability incurred with the use of these data or suggestions.

<sup>\*</sup> Specification values listed in our certificate of analysis